

## Product Data Sheet

# Uahard 3596T

Waterborne Polyurethane Curing Agent

### DESCRIPTION AND KEY PERFORMANCE PROPERTIES

Uahard 3596T是分散型异氰酸酯，适用于双组份水性聚氨酯涂料用的水性固化剂，可室温固化水性羟基树脂。粘度低，NCO含量高，具有较好的丰满度、光泽和硬度。

### SALES SPECIFICATIONS/技术指标

Appearance外观	水白透明	Particle Charge	阴离子
Solids Content 固含量/%	100	NCO /%	22±0.5
Viscosity 粘度/cps/25°C	1000-1500		

### TYPICAL CHARACTERISTICS/特点

具有较低的粘度，光泽高，丰满度好。交联密度高，具有良好的抗划伤性和耐化性。

### APPLICATION GUIDELINES/应用指南

双组份水性工业漆，木器漆和地坪漆，具有较低的粘度，可以实现厚涂。

### OPERATION INSTRUCTION/使用说明

- ① 可以与疏水性固化剂并用，提高漆膜厚度，不起泡
- ② 可与亲水性助溶剂任意比例混容
- ③ 需要稀释储存时，溶剂不能含羟基且需要氨基级，需要加 0.2-0.5%脱水剂

### PACKING AND SAVE/包装

- 25kg, 200kg;
- 储存在 5-30°C 环境中，为开盖下，储存期为 1 年
- 高温或者长时间接触空气会缩短保质期

The information contained in this document is based on trials carried out by our Technical centers and data selected from literature, but shall in no event be held or constitute or imply any warranty or undertaking, expressed or implied, or commitment on our part. Our formal specifications define the limit of our commitment. No liability whatever can be accepted by Copolymerline with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

联固精细化学有限公司

[www.uachemicals.com](http://www.uachemicals.com)

广州：广州市黄浦区荔香路 10 号和安堡商务中心 1—1313 室 电话：020-82277517 传真：020-82287484

上海：上海市闸北区广中西路 777 弄 99 号江裕大厦 806 电话：021-36696110 传真：021-36696100-8008

天津：天津市河东区新开路 42 号创智大厦 1-906 电话：022-24439106 传真：022-24439095